

KEMKO® 048

Marine Structure HiBuild Coat

Type:	Two-component, solvent-free, non-sag, epoxy resin / hardener.
Primary Use:	Coating concrete, steel and wood marine structures above and below the waterline.
Substrates:	Concrete, steel and wood. Dry, damp, wet, Immersed or submerged. Salt and fresh water environments.
Minimum Temp:	Installation: 50° F, Cure: 50° F (substrate temperature).
Color:	Base Coat : off-white; Top Coat : concrete gray (blue gray).
Application:	200 - 350 lineal feet/gallon (approx.) in crack sealing applications
Shelf Life:	Three years minimum in sealed containers (see below for conditions).

The properties listed in this bulletin are typical and descriptive of the product and should not be used for specification purposes. For specification preparation, reference the specification of this product available from ChemCo Systems, Inc. This product is available only through KIP System (KEMKO Injection Process) licensee/applicators.

Description: KEMKO® 048, Marine Structure HiBuild Coat is a two-component, solvent-free, epoxy coating designed for single coat application on concrete, steel and wood marine structures. It may be applied above or below the waterline and in both salt and fresh water environments. Typical applications include coating of concrete piers, seawalls, dock floors, drainage ditches, abutments, sewer and outfall pipes; protection of steel structure surfaces such as pilings, drilling rigs, production platforms, ship hulls, buoys, well jackets and bulkheads; and, protective coating of wooden structures such as pilings, piers, shelters and power poles.

Features: Unlike many other marine coatings, KEMKO 048 will bond to properly prepared dry, damp, wet, immersed and submerged substrates and cures to a tough, water resistant, impervious protective surface. The coating is freeze-thaw resistant and will not embrittle but will acquire a chalky surface when exposed to sunlight. KEMKO 048 is a 100% solids product and does not contain volatile organic solvents (VOC's). It has a convenient 2:1 (by vol.) Mixing ratio.

Limitations: The recommended minimum substrate temperature during application and cure is 50 deg F. In underwater and tidal zone applications, the coating may have to be applied within a relatively short period of time (30 minutes to several hours) after the substrate was cleaned to achieve an adequate bond. Wave action may displace the coating if exposure occurs before the coating has reached hard set. Do not add solvents or otherwise thin this material.

Packaging: Standard package sizes of Pan A + Pan B are 3, 15 and 150 gallon units.

Shelf Life: Three years minimum in unopened, original containers when stored between 60° and 90° F in a dry place away from sunlight. Remixing of components may be required upon long-term storage.

Chemical Resistance: KEMKO 048 provides excellent resistance to salt and fresh water, salt solutions, gasoline, kerosene, crude, fuel and mineral oil, most industrial waste solutions and many other chemicals. It has limited resistance to hydrocarbon solvents. Performance is a function of the specific chemical and concentration, ambient and solution temperature, exposure time and housekeeping procedures. For information on specific chemicals and exposure conditions, contact a ChemCo Systems, Inc., technical representative.

Color Selection: The standard color is off-white. Custom colors are available and may require minimum quantities and/or slightly higher cost.

Surface Preparation: Substrate surfaces may be dry, damp, wet, immersed or submerged but must be sound and free of all bond-inhibiting substances. Wet or dry sandblast to remove all loose and deteriorated substrate material, other surface contaminants such as tars, oils, paints, waterproofing materials, rust, barnacles, etc., that may interfere with the formation of a good bond. Cleaned concrete surfaces should have a minimum strength of 200 psi in direct tension. Steel surfaces should be cleaned to 'white metal' according to SSPC SP 5.

Mixing: KEMKO 048 is a two-component adhesive. The resin to hardener (Part A: Part B) mix ratio is 2:1, by volume. Read all material safety data (MSDS) information before handling the product. Wear safety glasses and clean neoprene rubber gloves when handling the materials. Premix the individual components before drawing from bulk packaging. Transfer the appropriate quantities of Part A and Part B into a mixing container. Use quantities that can be applied before the potlife of the mixed material expires. Blend thoroughly using a Jiffy mixer blade attached to a low speed (350 - 750 rpm) electric or pneumatic drill. Proper mixing will take 2 - 3 minutes. Do not mix the material underwater.

Installing:

Above the waterline: Use normal techniques applicable to viscous coating materials. Apply the material after the daily substrate temperature cycle has reached its peak. When the substrate is wet, use sufficient brush pressure to displace the water with the coating.

Below the waterline: Apply with a brush using slow deliberate motion and sufficient pressure to displace the water with the coating.

Clean up: Excess mixed product is best removed from the work area and tools before it hardens. Use of rags and solvents such as acetone or heavy-duty detergents facilitate cleaning. Cured product may be removed from tools by soaking in an epoxy stripper.



ChemCo Systems, Inc.
2800 Bay Road
Redwood City, CA 94063
Ph 650-261-3790 Fax 650-261-3799
www.chemcosystems.com

Typical Properties (1)

Property	Test Method	Value
Mix Ratio, A:B,	by vol	2: 1
	by wt	100: 24
Color:	Part A	VISUAL
	Part B	
	Mixed	
Weight per Gallon, lb:	Part A	ASTM D 1475
	Part B	
	Mixed	
Viscosity, poise:	Part A	ASTM D 2393
	Part B	
	Mixed	
Gel Time, 200 g, minutes	ASTM D 2471	25
Cure Time @ 68 F: soft gel, hours	CHEMCO	2.5
	hard gel, hours	3.0
	full cure, days	3
Bond Strength To Immersed ASTM C 109 Cement Mortar, psi (2)	ASTM D 4541	>200 (3)

(1) Cure schedule, 7 days at 73° ± 4° F and test temperature, 73° ± 4° F unless otherwise indicated.

(2) Test specimens conditioned, prepared and cured underwater (salt and fresh) at 68 F.

(3) Compressive strength of cement mortar, 4500 psi.

Handling and Toxicity: This bulletin does not accompany the product when sold. For hazard warnings, safe handling and first aid instructions.

READ CAREFULLY THE MATERIAL SAFETY DATA SHEETS AND CONTAINER WARNING LABELS.

Part A: Liquid epoxy resin, HMIS Health Hazard Rating- 2 (Moderate Hazard). Warning! Causes eye and skin irritation. May cause allergic skin reaction. Harmful if swallowed. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Avoid prolonged or repeated contact with skin.

Part B: Liquid epoxy hardener, HMIS Health Hazard Rating- 3 (Serious Hazard). Contains alkaline amines. Danger! Causes severe eye and skin burns. May cause allergic skin and respiratory reaction. Combustible, corrosive. Do not get in eyes or skin or on clothing. Avoid breathing vapor. Keep container closed. Use only with adequate ventilation. Wash thoroughly after handling. Keep away from heat and open flame.

DISCLAIMER: NO EXPRESS WARRANTY IS MADE WITH RESPECT TO THE RESULTS OF ANY USE OF THIS PRODUCT. NO IMPLIED WARRANTIES INCLUDING AND NOT LIMITED TO AN IMPLIED WARRANTY OF MERCHANTABILITY OR AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE ARE MADE WITH RESPECT TO THIS PRODUCT. NO LIABILITIES FOR PERSONAL INJURY, LOSS OR DAMAGE RESULTING FROM THE USE OF THIS PRODUCT IS ASSUMED. CHEMCO SYSTEMS, INC., RESERVES THE RIGHT TO ALTER OR DISCONTINUE THE PRODUCT DESCRIBED HEREIN AT ANY TIME AND WITHOUT PRIOR NOTICE.

KEMKO® and KIP System are trade names of ChemCo Systems, Inc.

Publication Number: 6 EP KEM-105L, Marine Structure HiBuild Coat

Publication Date: Nov. 1995