

## CCS™ GROUT, SUPERSEAL

### Very Fast Cure Epoxy Paste Adhesive For Crack Sealing Or Bonding

CCS Grout, SuperSEAL is a two - component, non-sag, deodorized mercaptan cure adhesive designed for surface sealing of non-moving horizontal, vertical and overhead cracks and delaminations in concrete, masonry, stone and sealed wood in preparation for repair with pressure injection equipment. The excellent handling characteristics and extremely fast cure of the product make possible application over a wide range of substrate temperatures and minimizes the interval between crack sealing and pressure injection. The buttery, non - sag consistency facilitates the measuring and mixing of small quantities and enhances applicator production rates. Contrasting component colors provides a visual key to proper proportioning and thorough mixing. CCS Grout, SuperSeal also may be used as a short working life/fast curing bonding adhesive for most construction materials and is ideally suited for bonding applications in cool and cold environments. The product is low in odor and may be considered for interior applications with adequate ventilation. The product may also be used at very low temperatures such as 35°F.

#### Features

- Convenient 1: 1, by vol. mix
- Short work life for fast cure and low temperature use
- Buttery consistency; non-sagging at applied thickness of 1/8 inch
- Bonds to dry and damp substrates
- Contrasting A and B component colors
- Low odor for interior applications
- Environmentally safe - No VOC solvents

**Limitations:** The recommended minimum substrate temperature during installation and for cure is 35 deg. F. **SuperSEAL has been specially formulated to minimize the odor of the sulfur-based accelerated hardener.** In warm weather, the short work life of the product may limit its usefulness.

**Packaging & Colors:** Standard package sizes of Part A & Part B is 2 gallons. Color is Concrete gray (blue-gray).

**Chemical Resistance:** Super SEAL has excellent resistance to a wide range of commonly encountered deicing chemicals, salts and aircraft and automotive fluids. It has limited resistance to hydrocarbon solvents. Performance is a function of the specific chemical and concentration, exposure times and housekeeping procedures. For information on specific chemicals and exposure conditions, contact a ChemCo Systems, Inc., technical representative.

**Surface Preparation:** Concrete surfaces may be dry or damp (not wet) but must be sound and free of all bond-inhibiting substances. Prepare surfaces in accordance with *ASTM D 4259* or *ACI 503R* and ChemCo Systems' specific recommendations. Cleaned concrete surfaces should have a minimum strength of 250 psi in direct tension. Steel surfaces should be cleaned to "white metal" according to SSPC SP 5.

**Mixing:** CCS Grout, SuperSeal is a two-component system. The resin to hardener (Part A : Part B) mix ratio is 1:1, by volume. Read all material safety data (MSDS) information before handling the product. Wear safety glasses and clean neoprene rubber gloves when handling the materials. Premix the individual components before drawing from bulk packaging. This product is a very short working life/fast-curing material; use quantities that can be applied before the working life of the material expires. For crack sealing applications, transfer the appropriate quantities of Part A and Part B onto a palette and manually mix with a margin trowel until streak-free and uniform in color. For bonding applications, transfer the appropriate quantities of Part A and Part B into a mixing container. Blend thoroughly using a Jiffy mixer blade attached to a low speed (350-750 rpm) electric or pneumatic drill.

**Installing:** For crack sealing applications, trowel a thin layer of material over the crack with a margin trowel, taking care to force material into the crack. Allow for adequate cure of the epoxy seal before beginning pressure injection of epoxy adhesive. For bonding applications, apply material on both surfaces to be bonded in thicknesses sufficient to fill all gaps between the two surfaces. Mate the surfaces and apply pressure until excess adhesive is extruded from the joint. Ideally, the material thickness at the bond line should be 1/32 - 1/8 inch. Surfaces must be mated while the adhesive is tacky. Allow for adequate cure of the epoxy adhesive before the bonded section is returned to service.

**Shelf Life:** Three years minimum in unopened, original containers when stored between 60 and 90 deg. F in a dry place away from sunlight. Remixing of components may be required upon prolonged storage.

**Clean up:** Excess mixed product is best removed from the work area and tools before it hardens. Use of rags and solvents such as acetone or heavy-duty detergents facilitate cleaning. Cured product may be removed from tools by soaking in an epoxy stripper.

**TYPICAL PROPERTIES <sup>(1)</sup>**

Property <sup>(2)</sup>		Test Method	Value
Mix Ratio, A:B,	by vol		1: 1
	by wt		100: 128
Color:	Part A	VISUAL	White
	Part B		Black
	Mixed		Concrete blue-gray
Weight per Gallon, lb:	Part A	ASTM D 1475	11.8
	Part B		11.8
	Mixed		11.8
Viscosity, p:	Part A	ASTM D 2393	5600
	Part B		440
	Mixed		3000
Non-Sag Thickness, inches		ASTM D 2730	1/4
Gel Time, 100 g, minutes	@ 40° F	ASTM D 2471	18
	@ 73° F		7
Compressive Yield Strength, psi		ASTM D 695	7800
Compressive Modulus, psi		ASTM D 695	315,000
Time To Bond Strength Greater Than ASTM C 109 Mortar, hours	@ 40° F	ASTM D 4541	1.15
	@ 73° F		0.75
Heat Deflection Temp, deg. F		ASTM D 648	110
Slant Shear Strength (bonded wet), psi (Cure schedule, 24 hours @ 73° F)		AASHTO T-237	Cement mortar failure (3)

- (1) The properties listed are typical and descriptive of the product and should not be used for specification purposes. For specification preparation, reference the ChemCo Systems, Inc., product guideline specification.
- (2) Cure schedule, 7 days at 73° ± 4 F and test temperature, 73° ± 4 F unless otherwise indicated.
- (3) Compressive strength of cement mortar, >4500 psi.

**Handling and Toxicity:** This bulletin does not accompany the product when sold. For hazard warnings, safe handling and first aid instructions, READ CAREFULLY THE MATERIAL SAFETY DATA SHEETS AND CONTAINER WARNING LABELS.

**Part A:** liquid epoxy resin, HMIS Health Hazard Rating - 2 (Moderate Hazard). Warning! Causes eye and skin irritation. May cause allergic skin reaction. Harmful if swallowed. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Avoid prolonged or repeated contact with skin.

**Part B:** Liquid epoxy hardener, HMIS Health Hazard Rating - 2 (Moderate Hazard). Contains polymercaptans. Warning! Causes eye and skin irritation. May cause allergic skin and respiratory reaction. Do not get in eyes or skin or on clothing. Avoid breathing vapor. Keep container closed. Use only with adequate ventilation. Wash thoroughly after handling. Keep away from heat and open flame.

**DISCLAIMER:** NO EXPRESS WARRANTY IS MADE WITH RESPECT TO THE RESULTS OF ANY USE OF THIS PRODUCT. NO IMPLIED WARRANTIES, INCLUDING AND NOT LIMITED TO AN IMPLIED WARRANTY OF MERCHANTABILITY OR AN IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE ARE MADE WITH RESPECT TO THIS PRODUCT. NO LIABILITIES FOR PERSONAL INJURY, LOSS OR DAMAGE RESULTING FROM THE USE OF THIS PRODUCT IS ASSUMED. CHEMCO SYSTEMS, INC., RESERVES THE RIGHT TO ALTER OR DISCONTINUE THE PRODUCT DESCRIBED HEREIN AT ANY TIME AND WITHOUT PRIOR NOTICE.

**CCS™ is a trade name of ChemCo Systems, Inc.**